AD-786 578

GAMMA-IRRADIATION DAMAGE IN AGE HARDENING AL ALLOYS

Nicholas F. Fiore

Notre Dame University

Prepared for:

Ballistic Research Laboratories

July 1974

BRL

AD

CONTRACT REPORT NO. 167

GAMMA-IRRADIATION DAMAGE IN AGE

HARDENING AL ALLOYS

Prepared by

University of Notre Dame
Department of Metallurgical Engineering
and Materials Science
Notre Dame, Indiana

July 1974

USA BALLISTIC RESEARCH LABORATORIES
ABERDEEN PROVING GROUND, MARYLAND

ib

43

ACCESSION for

NTIS   White Section   ☑
DDC   Buff Section   ☐
UNANNOUNCED   ☐
JUSTIFICATION

BY
DISTRIBUTION/AVAILABILITY CODES

Dist.   Avail and/or special

A

iC

REPORT DOCUMENTATION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER CONTRACT REPORT NO. 167	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER AD-786 578
4. TITLE (and Subtitle) GAMMA-IRRADIATION DAMAGE IN AGE HARDENING AL ALLOYS	5. TYPE OF REPORT & PERIOD COVERED FINAL	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Nicholas F. Fiore	8. CONTRACT OR GRANT NUMBER(s) DAAD05-70-C-0085	
9. PERFORMING ORGANIZATION NAME AND ADDRESS University of Notre Dame Dept of Metallurgical Eng & Materials Science Notre Dame, Indiana 46556	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS RDT&E 1T061102A33E	
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Ballistic Research Laboratories Aberdeen Proving Ground, Maryland 21005	12. REPORT DATE JULY 1974	
	13. NUMBER OF PAGES	
14. MONITORING AGENCY NAME & ADDRESS(If different from Controlling Office)	15. SECURITY CLASS. (of this report) UNCLASSIFIED	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	

16. DISTRIBUTION STATEMENT (of this Report)

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

Details of illustrations in
this document may be better
studied on microfiche

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Gamma Irradiation Damage
Aluminum Alloys
Internal Friction
Electron Microscopy

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

Pure Al and a series of age-hardenable Al alloys have been γ-irradiated in a Co^{60} source at a dose of 6×10^3 rads/min. Internal friction measurements have been made at 80 kHz by means of the Marx technique on samples _in situ_ during irradiation.

In Al and Al-3 w/o Cu, the damping decreases monotonically as is expected. The decrease is attributed to the immobilization of dislocations by the radiation-induced point defect pinners. In 2024-T6, 2017-T6 and Al-9.5 Mg, the damping

DD $_{1 \text{ JAN } 73}^{\text{FORM}}$ 1473   EDITION OF 1 NOV 65 IS OBSOLETE

Block 20. (cont'd)

passes through a minimum and begins an anomolous increase after 4 to 7 hours of irradiation.

Electron micrographs show that in Al and Al-3 w/o Cu, irradiation does not influence structure. In the alloys which display the damping minimum however, precipitate morphology changes during irradiation, with coarsening and/or de-coarsening and re-nucleation being observed.

The effect appears to depend upon the presence of Mg. Theory predicts that morphology changes can occur during γ-irradiation, with the mechanism being either Rutherford collision or Coulombic repulsion radiation damage.

TABLE OF CONTENTS

INTRODUCTION

Prior to about 1970, the literature on radiation damage in metals could be divided into two broad categories. One consisted of reports of basic damage mechanisms in pure metals and single phase alloys. The other consisted of empirical, rather than mechanistic studies of the properties of multi-phase engineering alloys. Consequently, most theoretical analyses of radiation damage mechanisms were based on data on materials which could not be used as structural components in a radiation environment.

The simple empirical documentation of properties of actual engineering materials has become inadequate as the nuclear environment has become more hostile e.g. in the fast breeder reactor. It has become necessary to understand materials' response to radiation so that selection and processing might be optimized.

An obvious example of the application of basic studies of damage in commercial materials is the investigation of swelling behavior of austenitic stainless steel fuel element cladding. Detailed theoretical modeling[1] based on thermodynamics and kinetics and rather refined transmission electron microscopy[2] analyses of defects have characterized the study. Recently the mechanistic approach has been extended to precipitation-hardenable Ni-base superalloys[3] since these multiphase materials appear to resist swelling more effectively than the stainless steels.

This report describes an experimental program directed toward an understanding of the mechanisms of γ-irradiation damage in another class of useful materials, precipitation-hardenable Al alloys. The potential engineering significance of this basic study is pointed out in Figure 1, which shows room-temperature

Charpy impact strength of alloy 2017, heat-treated to the fully-strengthened T6 condition. As the hardened alloy is γ-irradiated in a Co^{60} cell, a noticeable decrease in toughness is apparent. The trend, with each point representing the average of five tests, indicates that irradiation must influence structure since it influences properties. Gamma-irradiation is normally considered a rather mild radiation environment, so this suggests that it is dangerous to neglect it as being capable of influencing material behavior. It further suggests that intense neutron doses are not the only type of environment whose damage mechanisms must be understood.

The research program is directed toward answering several questions about the effect observed in Figure 1.

1. Is the effect real?

2. If it is real, what are the mechanisms of the structural changes causing property changes?

3. How can these mechanisms be controlled so as to guarantee the satisfactory performance of these materials in a γ or electron irradiation environment?

LITERATURE SURVEY

γ-Irradiation Damage Through Rutherford Collisions

The extent of crystalline damage caused by neutron, proton, or heavy-ion irradiation is enormous relative to that caused by direct electron or γ (indirect-electron) irradiation. Heavier particles cause long tracks of displaced atoms in the form of vacancies and interstitials, voids, and dislocation loops. This damage so overshadows that done by electrons that it is usually reasonable to neglect γ or electron irradiation as playing a role in influencing microstructure. As more evidence of morphology change from electron and γ-irradiation becomes available, the danger of this neglect becomes evident.

The solid state physicist and materials scientist usually think of radiation damage occuring because of Rutherford or "billiard ball" collisions between high energy particles and nuclei. An incoming particle transfers its momentum to an atom on a lattice site, displacing it and thereby causing crystal damage. The literature survey begins with a summary of this damage mechanism, although subsequent discussion will show that Rutherford collisions may not be the only relevant damage mechanism in multiphase alloys.

Of the multitude of references on γ-irradiation in metal crystals, the book by Chadderton[4] and the review by Sosin[5] present particularly complete treatments of the inter-relation between radiation absorption and crystal defect structure.

Chadderton points out that γ-rays may be absorbed and cause radiation damage by a number of processes. In the γ-energy range between 0.5 and 5 MeV, however, practically all absorption and damage in metals is caused by Compton electrons.[6] In the

Compton effect a γ-quantum strikes a free electron, transferring a portion of its kinetic energy (momentum) and causing the electron to move as a charged particle through the lattice. The energy of the electron is almost equal to that of the in-coming γ-ray, so the process produces projectiles capable of displacing atoms in the host lattice and causing radiation damage. Sosin refers to this process as "internal" electron irradiation, with the electron causing the Rutherford collision.

Collision mechanics shows that the electron of primary energy E_p can strike a host atom of mass M_2 and transfer energy up to T_m to it, where T_m and E_p are related by

$$T_m = \frac{2\,(E_p + 2m_e c^2)\,E_p}{M_2 c^2} \quad . \qquad (1)$$

Here m_e is the mass of the electron and c is the velocity of light.

For situations relevant to our work, the energy of the incident γ-ray is transferred to electrons which dissipate it in the form of heat and of radiation damage through point defect production. In order for point defects to be produced, T_m must be greater than E_d, the energy to displace an atom from a normal lattice site, or in some cases it must be greater than E_r, the energy to replace one lattice atom with another. The displacement mechanism of point defect creation requires that a struck atom or "knock-on" force its way through neighboring atoms and into an interstitial site.

In addition, in certain cases a Compton electron directs a knock-on directly toward a nearest neighbor, which the knock-on replaces in the lattice and directs in turn toward its nearest neighbor. In these situations, the displacement propagates down a chain until the process ends with the creation of an interstitial at a lattice discontinuity. The vacancy at the beginning of the

4

chain along with the interstitial at the discontinuity form a
separated Frenkel pair. This replacement mechanism of point
defect production requires energy E_r about 0.1 E_d, and Chadderton
shows that about five replacement pairs will be produced for each
displacement pair.

Since a 1 MeV γ-ray produces an electron of energy about
1 MeV, equation (1) indicates that energy T_m of 50 to 100 eV can
be imparted to an atom in a typical engineering alloy. Since E_d
is of order 10 eV, this energy is sufficient to produce one or
two displacement Frenkel pairs or several more replacement pairs.
It is apparent then that the radiation damage from Co^{60}
γ-irradiation should consist largely of single or small multiple
interstitials and vacancies distributed throughout the lattice.
One obvious effect of irradiation on morphology is the enhancement
of solute diffusion by these excess vacancies.

Further, it is reasonable to assume that the binding energy
of a solute atom in the precipitate is of order 10 eV, so that
either "knock-ons" or electrons can also be expected to sputter
atoms from the surface of precipitate particles. Moreover, the
precipitate presents a natural termination point for a displace-
ment propagation down a replacement chain in the lattice, so that
a higher concentration of matrix vacancies or of solute atoms
dissolved from precipitates can be expected at the periphery of
the particle.

In short, based on the usual models of radiation damage,
there is no reason to neglect the possibility that γ-irradiation
damage is capable of causing changes in second phase morphology
in a multiphase alloy.

5

Rutherford Collision Damage in Multiphase Alloys

Because most basic experimental radiation damage studies are
made in pure materials, there are few theoretical treatments of
the effect of irradiation on second phase particles. A fairly
recent review by Damask[7] summarizes the literature on this topic
and indicates that five precipitate-related processes can occur
when non-fissionable alloys are irradiated. They are: destruction
of order; change of precipitate size; enhanced nucleation; enhanced
diffusion; retarded diffusion. Damask concludes that electron
and γ-irradiation should influence only the last two processes.

A more recent paper by Nelson[8] et al similarly classifies
three simultaneously-occurring processes which can influence
precipitate morphology. The first is recoil dissolution or the
sputtering of atoms off precipitates by high energy particles.
The second is disordering dissolution in which impinging particles
destroy order on the periphery of an ordered precipitate and cause
it to dissolve. The third is enhanced diffusion due to excess
vacancies generated during irradiation. The authors, conclude
(without experimental evidence) that only the last process will
be operative in γ or electron irradiation.

Nelson et al consider the net effect of irradiation on
spherical, ordered precipitates of volume $V = 4\pi r^3/3$. There are
N atoms per unit volume in the precipitates, and each atom can be
displaced by irradiation at a damage rate of K displacements/atom/
sec.

The precipitates grow or shrink by a vacancy diffusion mecha-
nism. The normal diffusivity D can be supplemented with an
enhanced diffusivity D', which comes about as radiation-induced
vacancies increase atom mobility. For materials of low dislocation
density

$$D' = \lambda^2 \left[\frac{K\, \nu_s}{z} \right]^{\frac{1}{2}} \qquad (2)$$

where λ is the jump distance, ν_s is the solute (vacancy) jump frequency, and z is a recombination parameter $\cong$ 1.

As far as the precipitates themselves are concerned, recoil dissolution sputters atoms into the matrix at a flux $\varphi \cong 10^{14}$ K/ cm²/sec. The flux causes the precipitate to decrease in volume at a rate

$$\frac{dV}{dt} = - \frac{4\pi r^2 \varphi}{N} .$$ (3)

If the precipitate is ordered, the irradiation particles disorder a shell of thickness ℓ, on the periphery. A fraction q of the atoms in the shell will leave the precipitate and dissolve in the matrix, a process characterized by the dissolution parameter $\psi = \ell$ q. The rate of volume change due to this effect is

$$\frac{dV}{dt} = - 4\pi r^2 \psi K.$$ (4)

The kinetics of the processes are defined by the diffusivity D'' = D+D', which is employed in the three simultaneous differential equations which govern particle growth or shrinkage The equations are

$$\frac{dV}{dt} = 3D'' C_2 r/p,$$ (5)

$$\frac{dr}{dt} = - \frac{\varphi}{N} + \frac{3D''C_1}{4\pi pr} - D'' r^2 n,$$ (6)

and

$$\frac{dr}{dt} = - \psi K + \frac{3D''C_1}{4\pi pr} - D'' r^2 n.$$ (7) .

7

Here C_1 is the total solute content of the system, C_2 is the matrix solute concentration, p is the atom fraction of solute in precipitates and n is the number of precipitates per unit volume.

Analytical solutions to the three equations show that the behavior of the system is very complicated. Depending on the values of the various parameters involved:

1. Precipitates below a critical size may grow, while those above that size may shrink, i.e., simultaneous coarsening and decoarsening may occur.

2. Re-solution may so enrich the matrix in solute that nucleation of a fine dispersion of precipitates may be super-posed on shrinkage and growth of larger precipitates.

In general, the system responds to irradiation in a much more complex fashion than is observed in typical thermal-mecha-nical treatments. However, the magnitude of change of precipi-tate size resulting from the processes described by equations 2 through 6 can be estimated from the equations themselves. Consider as the most typical example, Al-Cu alloys in which the precipitate responsible for maximum hardening[8], θ', is an ordered platelet, tens of $\overset{\circ}{A}$ngstroms thick and several hundred $\overset{\circ}{A}$ngstroms in diameter. Represent the precipitate as a sphere of $r = 10^{-6}$ cm and note that our internal friction measurements in Cu show that Co^{60} γ-irradiation at a dose of 1×10^2 rads/sec produces damage at a $K = 2 \times 10^{-13}$ displacements/atoms/sec. For these precipitates, the recoil mechanism described by equation (3) produces a rate of volume change

$$\frac{dV}{dt} \overset{\sim}{=} 10^{-33} \text{ cm}^3/\text{sec (recoil dissolution)}.$$

This corresponds to a rate of radius change dr/dt of about 10^{-11} cm/sec. For an irradiation time of 10 hours (3.6×10^4 sec), a

8

net radius change of $10^{-8} - 10^{-9}$ cm can occur. Thus reasonable irradiations result in changes in the order of monolayer in the precipitate size.

The disordering dissolution mechanism requires that the dissolution parameter $\psi = \ell q$ be estimated. It is reasonable that a γ-induced electron can disorder a region ℓ, at least one atomic diameter (10^{-8} cm) in depth. Assuming further that the probability q of atom leaving the disordered region rather than moving to re-order it is 0.1, then $\psi = 10^{-9}$ cm. For a precipitate of radius 10^{-6} cm, equation (4) predicts

$$\frac{dV}{dt} = 10^{-38} \text{ cm}^3/\text{sec (disordering dissolution)}.$$

Since the GP zones in these alloys are ordered, a typical γ-irradiation treatment will remove an additional monolayer from the precipitates.

These relationships show that γ-induced electrons can bring about measurable changes in precipitate size. It remains to ask whether significant changes are possible kinetically i.e. whether D' is large enough to allow significant solute atom transport. Assuming that $\lambda = 3 \times 10^{-8}$ cm and that $\nu_s = 10^7$ /sec (both typical values) then equation (2) yields,

$$D' = 10^{-18} \text{ cm}^2/\text{sec (enhanced diffusion)}.$$

In his discussion of aging in Al-Cu, Fine[10] notes that D for Cu in Al at 300° K is 10^{-25} cm²/sec, a value much too small to account for observed precipitation. He further mentions that excess vacancies introduced by quenching from the solutionizing temperature cause an enhanced diffusion coefficient $D' = 10^{-18}$ cm²/sec to exist. This value is adequate to cause change in precipitate size at 300-400°K. Since D' due to quenching is of identical order of magnitude to that due to γ-irradiation, it can be concluded that favorable kinetic conditions exist for change of precipitate size during irradiation.

9

The theoretical predictions all indicate that γ-irradiation can influence microstructure, although conservative use of the predictions suggests that the influence will be very small. The following section of the literature review shows that the Coulombic repulsion of ions, ionized by high energy radiation, can bring about greater damage in multiphase materials than can the Rutherford collisions just considered.

Coulombic Repulsion Damage in Multiphase Alloys

In 1950, Varley[11] showed that the concentration of point defects produced in alkalai halides by X-irradiation exceeded that predicted for Rutherford collisions by several orders of magnitude. He proposed that a much more significant cause of irradiation damage was the repulsion of like-charged ions created by X-rays. Specifically he noted the high probability of the reaction

$$Cl^- + h\nu \ (X-ray) \rightarrow Cl^+ + 2e^-, \qquad (8a)$$

followed by the dissociation of a small region in the alkalai halide lattice through the Coulombic repulsion

$$Cl^+ + M^+ \rightarrow Displacement\ of\ M\ and\ Cl, \qquad (8b)$$

where M denotes an alkalai metal.

This type of reaction can occur only in poor electrical conductors, because the electrons created by the reaction(8a) remain detached from their parent ion for a time sufficient for displacement to occur only in poor conductors. In metals, the electrons immediately return to the parent ion, or free electrons in the metal electron "gas" rush to the ion so rapidly that the ion cannot be repelled from the equilibrium position by the like charges or its neighbors. It might be expected then that this Coulombic reaction can only cause radiation damage in metals which contain poorly-conducting second-phase particles; e.g. oxides, non-metallic inclusions or certain intermetallic compounds.

10

Ten years later, Platzman[12] showed that ionization and therefore, repulsion, might occur easily by the Auger effect in which impinging radiation increases the over-all energy of an atom to such an extent that electrons are emitted in a so-called "Auger-cascade." Loss of electrons causes the atom to become charged, and if the charge is of the same sign as that of neighboring ions, the parent ion is repulsed to an interstitial site, leaving a vacancy in the original position. Not only are point defects created by this mechanism, small precipitate particles can be literally shattered apart by Coulombic repulsion in certain cases.

Both the Varley and the Platzman mechanisms require that primary radiation dissipate its energy in causing electrons to be ejected from atoms rather than by causing secondary (flourescent) radiation to be created. It can be shown[13] that the tendency of an irradiated atom to emit electrons rather than flourescent radiation is proportional to $[1 + (Z/30)^4]^{-1}$, where Z is the atomic number. It is evident that the lighter the atom, the greater the ionization tendency, and the greater the susceptability to radiation damage through Coulombic repulsion. This suggests that poorly-conducting second phase particles containing light atoms might be especially prone to radiation-induced morphology change.

In any event, it is evident that radiation damage theory predicts that the second phase particles in an engineering alloy can be influenced by γ-irradiation. The conventional "billiard-ball" collision mechanism can account for changes in precipitate size, shape, and number density, through enhanced diffusion, recoil dissolution, or disordering dissolution. The Coulombic repulsion mechanism can lead to dissolution of poorly-conducting second phase particles through either direct ionization (Varley) or Auger ionization (Platzman) events.

11

The next section of the report shows that internal friction provides an ideal tool for the study of these radiation damage processes, and the section following it describes the experimental results.

EXPERIMENTAL RESULTS

Damping Studies of Precipitation in Al-Cu

It is well known that internal friction measurements provide an extremely sensitive tool for the study of atomistic processes within solids, including recovery, radiation damage and precipitation. In a recently-published work[14] we have shown that ultrasonic pulse echo attenuation measurements in the MHz frequency range and resonance bar damping measurements in the kHz range allow accurate monitoring of the aging process in Al-3 Cu.

The pulse-echo method allows the measurement of the decay or attenuation (α) of a high frequency elastic wave pulse as it reverberates between parallel surfaces within a plate-like sample[15]. The resonance bar method, as conducted with the Marx[16] technique, allows the measurement of the energy loss or damping (δ) which occurs in a sample driven at resonance by quartz transducers. Both internal friction techniques are carried out with sample being aged and/or γ-irradiated in situ, and both allow measurement of modulus defect, another gage of internal friction.

Figure 2 shows the behavior of ultrasonic attenuation and resonance bar damping during aging at 190°C of solution treated Al-3 Cu. Included in the figure is a plot of the Rockwell "E" hardness of the material as a function of aging time, t. It is seen that both techniques provide a sensitive gauge of the sub-microstructural and microstructural changes which occur during aging and which influence macroscopic properties.

In addition to yielding a direct qualitative measure of atomic processes taking place within the alloys, the measurements can be interpreted quantitatively so as to give insight as to the mechanisms responsible for the processes.

For example, Figure 2b shows α as a function of t and frequency (f). It is possible to divide α (f, t) into the component

parts which each individual internal friction process contributes to the observed loss. A background loss α_b (t), which can be shown to be independent of t, arises because of extraneous effects and because of scattering by grain boundaries within the polycrystalline sample. A precipitate scattering loss α_s (t), which depends upon precipitate size and shape and is independent of f in these experiments, occurs as precipitates, even of those of sub-microstructural size, scatter the elastic wave. A dislocation loss α_d arises because dislocations oscillate under the action of the vibratory elastic wave and dissipate energy. (Application of the Granato-Lucke[17] theory of dislocation damping to these experiments indicates that this latter loss should vary as f^2 and consist of a time-dependent component $\alpha_d(f^2, t)$ and a time independent component $\alpha_d(f^2)$.) The total attenuation is

$$a(f,t) = \alpha_b(f) + \alpha_d(f^2) + \alpha_s(t) + \alpha_d(f^2, t). \qquad (9)$$

The time-dependent portion of the attenuation, $\Delta\alpha$, gives a measure of the kinetic processes occurring during aging and consists of a frequency-dependent dislocation contribution and a frequency-independent scattering contribution; thus

$$\Delta\alpha = a(f,t) - \left[\alpha_b(f) + \alpha_d(f^2)\right] = \alpha_s(t) + \alpha_d(f^2, t) \qquad (10)$$

Plots of $\Delta\alpha$ versus f^2 for various aging times should yield straight lines if this analysis is valid. The intercepts are equal to α_s (t) and should give a direct measure of changing precipitate size and/or shape. The slopes should be proportional to the changing dislocation component of the internal friction as dislocations become either more pinned or more mobile as precipitates form and remove solute from the matrix.

Figure 3a shows such plots for aging times to 250 hours. They are indeed linear, with intercepts and slopes increasing

14

with t. Figure 3b shows the intercepts α_s (t) plotted against independent measurements of G. P. zone diameter obtained as a function of t. The correlation between the two is evident.

Our damping studies of aging in the absence of radiation have shown that:

1. Change of precipitate size and/or shape can be followed and analyzed quantitatively by means of internal friction experiment and theory.

2. The change in the dislocation damping of an alloy undergoing structural change provides a gauge of the processes causing change, and insight regarding the mechanisms of the processes can be gained through application of damping theory.

Irradiation-Damping Studies

Because the experiments just discussed have shown damping
measurements to be a sensitive gauge of precipitation-related
phenomena, the techniques have been applied to fully hardened
Al alloys subjected to γ-irradiation in the 14 kilocurie Co^{60}
γ source of the University's radiation laboratory. Emphasis
has been on the use of the Marx resonance bar technique, with
polycrystalline rod samples vibrated at 80 kHz in the fundamental
longitudinal mode.

Figure 4 shows the _in situ_ damping of a 99.99% pure Al sam-
ple irradiated at a dose of $I \times 10^2$ rads/sec. The sample was
put through a heat treatment corresponding to the T6 condition
for direct comparison with alloy samples. (Solution heated at
$500^{\circ}C$, quenched, aged at $190^{\circ}C$ for 10 hours.) The decrease in
the damping noted has been observed often in single phase materi-
als during electron and γ-irradiation. It is attributed to the
decrease in the dislocation contribution to the internal friction,
as the point defects created during irradiation migrate to dislo-
cations, immobilize them, and eliminate their ability to oscillate
and dissipate vibrational energy. The accompanying increase in
resonance frequency f_r with decrease in damping is consistent
with the relationship of modulus defect to damping. Stern and
Granato[18] have conducted extremely detailed experiments in the γ-
irradiation of single-phase materials and have provided detailed
analysis of the damping results in terms of dislocation damping
theory. Our observations are consistent with theirs and certainly
are not surprising.

Figure 5 shows that high-purity Al - 3 $^W/_o$ Cu in the T-6
condition responds to irradiation in a manner similar to pure
Al, with a monotonic decrease in δ and its corresponding in-
crease in f_r. Both pure Al and the binary alloy then exhibit
behavior consistent with the usual dislocation pinning model
of irradiation - damping experiments.

On the other hand, surprising results are obtained during
γ-irradiation of commercially pure 2017-T6 and 2024-T6, Figures
6 and 7. The usual decrease in δ is observed during the first
7 hours of irradiation, presumably because radiation-induced
point defect pinners are immobilizing dislocations. At longer
times however, δ begins to increase and approach a saturation
value. The decrease in f_r which should accompany the unusual
increase in δ is observed.

Table I lists the nominal compositions of the commercial
alloys. One major difference between them and the pure Al or
the Al - Cu binary alloy is the presence of Mg, which is a light

Table I

Nominal Compositions of Commercial Al Alloys

Alloy	Wt% Cu	Wt% Mg	Wt% Mn
2017	4.0	0.5	0.5
2024	4.5	1.5	0.5

element and an extremely potent oxide former. This suggests that
Mg - bearing alloys might be especially susceptible to radiation
damage by way of the Varley-Platzmann mechanism.

In order to determine if the presence of Mg is related to the
anomalous damping minimum observed in the commercial alloys. Measure-
ments have been conducted on a high purity binary Al - 9.5 $^W/_o$ Mg

17

donated by ALCOA. The alloy, which is known to age harden slug-
gishly is solution-treated at 530° C for 2 hours, quenched and
aged at 190° C for 12 hours. Its damping is then determined <u>in</u>
<u>situ</u> during irradiation with the Marx gauge. Figure 8 shows
that indeed, a damping minimum appears after 4 hours of γ-irradi-
ation, indicating that the unusual behavior is somehow associated
with Mg.

One major disadvantage of the damping measurements summarized
in Figures 4 through 8 is that they are indirect and do not give
a clear indication of the effect of irradiation on precipitate
morphology. For that reason, transmission electron micrographs
of both the unirradiated and irradiated materials have been ob-
tained.

Figure 9 shows pure Al in the as-heat treated condition and
after 7 and 25 hours of γ-irradiation. The original appearance
is that of a single phase material of low dislocation density.
After 7 hours of irradiation, small spots, which are probably ra-
diation-induced dislocation loops, appear in the microstructure,
and their density increases during subsequent irradiation to 25 hours.

It might be expected that the loops, which increase dislocation
density, could cause an increase in dislocation damping. This is
evidently not the case since Figure 4 shows a monotonic decrease
in δ during irradiation. The micrographs along with the damping
data shows that pure Al has a very predictable response to irradia-
tion.

The microstructure of Al - 3 Cu in the T6 condition as shown
in Figure 10 after 0, 7 and 25 hours of irradiation are quite si-
milar. The precipitates are flat plates of a general square shape,

18

about 1000 $\overset{o}{A}$ in long dimension and roughly 10 $\overset{o}{A}$ thick. The size, shape and number density of particles remain unchanged during irradiation, and this is consistent with the damping data which show the steady decrease in δ characterizing simple dislocation pinning.

Both Figures 9 and 10 then indicate that no significant microstructural changes occur when the unusual minimum in damping is absent. Figure 11 shows electron micrographs of 2017-T6 after 0, 7 and 25 hours of irradiation. The as-age hardened structure consists of a profuse distribution of fine precipitates in the matrix. The high precipitate number density of 6×10^{10} per cm^2 is to be expected for a commercial alloy, designed to show marked strengthening. After 7 hours of irradiation, a time corresponding to the minimum in δ, precipitate coarsening occurs. The 25 hour irradiation produces a fine dispersion of precipitates similar to the original one. The combined coarsening-decoarsening predicted by Nelson et al. has taken place, and is characterized by the internal friction minimum.

The damping minimum also appears in the Al - 9.5 Mg alloy, whose microstructure is shown in Figure 12. The unirradiated but age-hardened material shows little evidence of precipitation. This is consistent with the known sluggishness of precipitation in this binary alloy.[19] Little if any change in microstructure is observed after 4 hours of irradiation, the time working the minimum in δ. After 25 hours of irradiation however, a time adequate for the damping to pass through the minimum and return to a high value, a profuse precipitation of fine discs is observed. Once again it is seen that the damping minimum is an indicator of radiation-induced morphological changes.

19

Thus far it has been seen that radiation damage theory, based on either Rutherford collision or Coulombic repulsion models, predicts that γ-irradiation can influence the microstructure of a multiphase alloy. Further both damping measurements and electron microscopy indicate that change can be brought about in certain Al alloys.

CONCLUSIONS

The INTRODUCTION to this report sets three major experimental objectives. The first is to establish whether γ-irradiation can cause morphology change. The second is to explain the reason that irradiation influences morphology. The third is to develop suggestions for the control of material behavior in a γ-irradiation environment. The first objective has been met with good success, and the second and third have been partially met.

The Existence of an Effect

Both Rutherford collision and Coulombic repulsion theory indicate that γ-irradiation should influence the size, shape and distribution of precipitates in multiphase alloys. The respective theories are not clear as to the extent of the influence, but first estimates suggest that the effect should be small. Usual treatments of radiation damage, in fact, completely neglect γ-irradiation damage as being capable of exerting significant effects on structure and properties. The damping and microscopy results show independently that microstructural changes do occur.

The increase in δ after a critical period of irradiation may be logically attributed, at first thought, to the increase in dislocation density in the materials as radiation-induced dislocation loops are formed. This explanation is inadequate however because neither pure Al or Al - 3 $^W/_O$ Cu show the minimum although there is evidence that loops are forming.

The internal friction minimum can only be interpreted in terms of a net freeing of dislocations of solute atom pinners after a critical irradiation dose. This implies a net transfer of solute atoms from Cottrell atmospheres into the matrix or into precipitates.

21

The electron micrographs indicate that the transfer is into precipitates since second phase morphology changes after the critical irradiation dose. There is no doubt that γ-irradiation changes the microstructure of certain of these materials.

Mechanisms of the Effect

The reasons behind the observed effects are not evident. Enhanced diffusion and nucleation may be playing a part in the kinetic processes. Direct shrinking of precipitates because of Rutherford collisions may be occurring. Precipitate break-up because of Coulombic effects may be taking place. More in-depth studies in systems with alloying elements of a range of Z and oxide-forming tendencies are necessary. Further kinetic studies yielding the time dependence of precipitate growth and/or shrinkage are necessary to establish the roles of enhanced diffusion or nucleation.

Property Control in a γ-Irradiation Environment

At this point in the investigation it is evident that Mg plays an important part in an alloy's susceptibility to γ-irradiation damage. Its presence should be avoided until such time that the clear relationship between structure, properties and γ-irradiation in these alloys is determined.

REFERENCES

1. S. D. Harkness and C. Y. Li, "Theoretical Study of Swelling of Fast Neutron-Irradiated Materials," Argonne National Laboratory, Report 7588 (1969).

2. C. Cawthorne and E. J. Fulton, Nature, 216 757 (1967).

3. C. F. Bilsby and J. Standring, "Neutron Irradiation and Coarsening Kinetics of γ', " TRG Report 2113, 1971.

4. L. T. Chadderton, Radiation Damage in Crystals, (John Wiley, New York, 1965).

5. A. Sosin, Adv. in Mats. Res. 2, 159 (1968).

6. O. S. Oen and D. K. Holmes, J. Appl. Phys., 30, 1289 (1959).

7. A. C. Damask in Radiation Effects, W. F. Sheely ed. (Gordon and Breach, New York, 1967) p. 77.

8. R. S. Nelson, J. A. Hudson, and D. J. Mazey, "Stability of Precipitates in an Irradiation Environment," AERE Report R7120, 1972.

9. J. M. Silcock, T. J. Heal, and H. K. Handy, J. Inst. Met. 82, 239 (1953).

10. M. Fine, Intro. to Phase Transformations, (MacMillan, New York, 1964) p. 109.

11. J. H. O. Varley, J. Nuc. Energy, 1, 130 (1954).

12. J. Durup and R. L. Platzman, Disc. Far. Soc. 31, 156. (1961).

13. E. V. Candon and H. Odishaw in Handbook of Physics, (McGraw-Hill, New York, 1958), p. 124.

14. N. F. Fiore and S. K. Gupta, Met. Trans., 2, 1065 (1971).

15. R. Tuell, C. Elbaum, and B. Chick, Ultrasonic Methods in Solid State Physics, (Academic Press, New York, 1969).

16. J. Marx, Rev. Sci. Instr., 22, 503 (1951)

17. A. Granato and K. Lücke, J. Appl. Phys., 27, 583 (1956).

18. R. M. Stern and A. Granato, Acta Met., 10, 358 (1902).

19. A. Kelly and R. B. Nicholson, Prog. in Mat. Sci., 10, 151 (1962).

LIST OF FIGURES

Table I   :

Table I   Nominal Compositions of Commercial Al Alloys

Figure 1. Toughness of 2017-T6 as a function of Co^{60} γ-irradiation dose. (Each point represents average value of 5 impact tests).

2a. Rockwell E hardness versus ageing time at 190°C.


2b. Ultrasonic attenuation versus ageing time at 190°C.

2c. Resonance bar damping versus ageing time at 190°C.

Figure 2.   Sensitivity of internal friction measurements to micro-
structural changes in Al - 3 w/o Cu.

30

3a. Separation of dislocation damping and precipitate scattering
components of ultrasonic attenuation.

3b. Attenuation due to precipitates versus precipitate size.

Figure 3. Analysis of ultrasonic measurements of ageing of
Al - 3 w/o Cu at 190°C.

Figure 4. Effect of γ-irradiation on damping (δ) and resonance frequency (f_r) of 99.99% pure Al.

Figure 5. Effect of γ-irradiation
on damping (δ) and reso-
nance frequency (f_r) of
Al-3 w/o Cu.

Figure 6. Effect of γ-irradiation on damping (δ) and resonance frequency (f_r) of 2017-T6.

34

Figure 7. Effect of γ-irradiation on damping (δ) and resonance frequency (f_r) of 2024-T6.

Figure 8. Effect of γ-irradiation on damping (δ) and resonance frequency (f_r) of Al-9.5 w/o Mg.

Figure 9

(a) 99.99% Al. Unirradiated

(b) 99.99% Al. Irradiated 7 hours at a Co^{60} γ dose of 6 x 10^3 rad/min.

(c) 99.99% Al. Irradiated 25 hours at a Co^{60} γ dose of 6 x 10^3 rads/min.

37

Figure 10

(a) Al-3 w/o Cu. Unirradiated.

(b) Al-3 w/o Cu. Irradiated 7 hours at a Co^{60} γ dose of 6×10^3 rads/min.

(c) Al-3 w/o Cu. Irradiated 25 hours at a Co^{60} γ dose of 6×10^3 rads/min.

38

Figure 11

(a)   2017-T6 Unirradiated.

(b)   2017-T6 Irradiated 7 hours at a Co^{60} γ dose of 6 x 10^3 rads/min.

(c)   2017-T6 Irradiated 25 hours at a Co^{60} γ dose of 6 x 10^3 rads/min.

39

Figure 12

(a) Al-9.5 w/o Mg. Unirradiated.

(b) Al-9.5 w/o Mg. Irradiated 4 hours at a Co^{60} γ dose of 6×10^3 rads/min.

(c) Al-9.5 w/o Mg. Irradiated 25 hours at a Co^{60} γ dose of 6×10^3 rads/min